

Athletic Shoes Midsole

Consumer goods

Print Date: 2025-12-05

Benefits

- Application requirements:
- Stability
- Lightweight
- Energy rebound
- Long lifetime
- Material properties:
- Low crystallization speed and temperature
- High elongation at break
- Arnitel E-TPEE is thermoplastic and can be fully recycled



Details

Very high rebound rate: 75–80% ;High rebound/density ratio;Consistent performance in all climate conditions;Low compression set;Colorability;Recyclable

Products

Arnitel® ECO L460
TPC

Arnitel® ECO L400
TPC

Arnitel® FM8226
TPC-ET

Arnitel® FM8686
TPC-ET

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.