

Arnite® A

PET

Print date: 2024-02-28

Introduction:


Arnite® A polyesters are available in various grades. The main difference is the viscosity. Extrusion (single screw) of Arnite® A is possible with a conventional 3 zone screw with a compression ratio between 2.5 and 3.2. A barrier screw in combination with a grooved barrel results in an optimal stable process.

Material handling:

Pre-drying of Arnite® A grades is essential for extrusion application. Therefore we recommend minimum 4 hours drying at 140 °C. Please refer table mentioned below. A desiccant dryer with a dew point of ≤ -30 °C should be used (airflow rate: 2,5-3,0 m³/kg.hr) in order to reach a moisture level below 50 ppm (0,0005%). A drying hopper should be applied to the extruder.

Processing:

Arnite® A extrusion grades are run at mass temperatures between 270 and 280 °C depending on machine and material choice. Extrusion type Arnite® T grades should be processed with low moisture content (< 50 ppm) to keep manufacturing stable. The machine parameters can be changed in order to meet the required stability and melt temperature.



All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2023. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Arnite® A

Print date: 2024-02-28

Table 1. Typical temperature settings for Arnite® A extrusion (°C)

Grade Name	Zone 1	Zone 2	Zone 3	Zone 4	Die	Melt	Pre-Drying
Arnite® A02 307	285-295	270-280	265-275	265-275	265-275	270-280	80-120

Application:

Arnite® A02 307 is a low viscosity extrusion grade; it is convenient typical extrusion and master batch type of applications and can also be used in Food application come into contact. The product is widely used in the filter of paper clothing machine

Safety:

Please handle the material with care. Follow all guidelines indicated on the temporarily version of the SDS.

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2023. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.