

Akulon[®] AKV30FN04UF DUS867

 Akulon[®] SG-KGS6/HV

PA66-GF30 FR(40)

30% Glass Fiber Reinforced, High Flow, Halogen free and free of red phosphorous

Print Date: 2026-03-06

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.28 / *	%	ISO 294-4
Molding shrinkage (normal)	1.31 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	11000 / 8600	MPa	ISO 527-1/-2
Stress at break	155 / 120	MPa	ISO 527-1/-2
Strain at break	3 / 3.4	%	ISO 527-1/-2
Flexural modulus	11500 / 7450	MPa	ISO 178
Flexural strength	240 / 180	MPa	ISO 178
Charpy impact strength (+23°C)	68 / 62	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	50 / 48	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 10	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 10	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	247 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.21 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.67 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Akulon[®] AKV30FN04UF DUS867

Akulon[®] SG-KGS6/HV

Print Date: 2026-03-06

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Burning Behav. at 0.75 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.4 / -	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	3 / -	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	800 / -	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	0.4 / -	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	825 / -	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	3 / -	mm	IEC 60695-2-13
ELECTRICAL PROPERTIES		DRY / COND	
Relative permittivity (100Hz)	4.2 / 7.3	-	IEC 62631-2-1
Relative permittivity (1 MHz)	3.9 / 4.3	-	IEC 62631-2-1
Dissipation factor (100 Hz)	110 / 110	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	150 / 490	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / 5E12	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15 / 3E13	Ohm	IEC 62631-3-2
Electric strength	41 / 38	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	V	IEC 60112
OTHER PROPERTIES		DRY / COND	
Water absorption	4.9 / *	%	Sim. to ISO 62
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1430 / -	kg/m ³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.