

Akulon[®] Diablo HDT2504BM

(PA66+PA6)—GF20

20% Glass Fiber Reinforced, Heat Stabilized, Blow Molding Grade

Print Date: 2025-10-04

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	7000 / 3600	MPa	ISO 527-1/-2
Stress at break	125 / 57	MPa	ISO 527-1/-2
Strain at break	3.5 / 20	%	ISO 527-1/-2
Flexural modulus	5700 / 2750	MPa	ISO 178
Flexural strength	195 / 85	MPa	ISO 178
Tensile modulus (200°C)	1600	MPa	ISO 527-1/-2
Stress at break (200°C)	37	MPa	ISO 527-1/-2
Strain at break (200°C)	13	%	ISO 527-1/-2
Charpy impact strength (+23°C)	72 / 95	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	63 / 41	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 14	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	6 / 3	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	255 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.3 / *	E-4/°C	ISO 11359-1/-2
OTHER PROPERTIES			
	DRY / COND		
Humidity absorption	2.6 / *	%	Sim. to ISO 62
Density	1270 / -	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.