

Akulon[®] F136–DH

PA6

High Viscosity, Nucleated, Heat Stabilized, Tube Extrusion

Print Date: 2025–10–04

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES		VALUE	
Tensile modulus	3150	MPa	ISO 527–1/–2
Nominal strain at break	45	%	ISO 527–1/–2
Yield stress	85	MPa	ISO 527–1/–2
Yield strain	4	%	ISO 527–1/–2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5.5	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES		VALUE	
Melting temperature (10°C/min)	220	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	60	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	170	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	1	E–4/°C	ISO 11359–1/–2
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	1.5	mm	IEC 60695–11–10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	3	mm	IEC 60695–11–10
ELECTRICAL PROPERTIES		VALUE	
Relative permittivity (100Hz)	3.4	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3.1	–	IEC 62631–2–1
Dissipation factor (100 Hz)	65	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	165	E–4	IEC 62631–2–1
Volume resistivity	>1E13	Ohm*m	IEC 62631–3–1

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Akulon[®] F136–DH

Print Date: 2025–10–04

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Electric strength	25	kV/mm	IEC 60243–1
Comparative tracking index	600	V	IEC 60112
OTHER PROPERTIES	VALUE		
Water absorption	9.5	%	Sim. to ISO 62
Humidity absorption	2.5	%	Sim. to ISO 62
Density	1130	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	VALUE		
Viscosity number	245	cm³/g	ISO 307, 1157, 1628

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.