

Akulon® K224-PG3

PA6-I-GF15

15% Glass Reinforced, Impact Modified

Print Date: 2024-10-15

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	DRY / COND		
Molding shrinkage [parallel]	0.4 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1/*	%	Sim. to ISO 294-4
MECHANICAL PROPERTIES	DRY / COND		
Tensile modulus	5400 / 2600	MPa	ISO 527-1/-2
Stress at break	105 / 60	MPa	ISO 527-1/-2
Strain at break	4 / 15	%	ISO 527-1/-2
Charpy impact strength (+23°C)	70 / 90	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	70 / 70	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	16 / 25	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	9/9	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES	DRY / COND		
Temp. of deflection under load (1.80 MPa)	185 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	205 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	3.6 / 14	_	IEC 62631-2-1
Relative permittivity (1 MHz)	3.3 / 4.5	_	IEC 62631-2-1

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or

Selier represents and warrants exclusively that on the date of delivery by selier the product shall be in comorning with the specifications agreed upon selections agreed upon selections of warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Akulon® K224-PG3

Print Date: 2024-10-15

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Dissipation factor (100 Hz)	100 / 1500	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	180 / 1200	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	-/> 1E15	Ohm	IEC 62631-3-2
Electric strength	25 / 20	kV/mm	IEC 60243-1
Comparative tracking index	-/500	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Water absorption	6.8 / *	%	Sim. to ISO 62
Humidity absorption	2/*	%	Sim. to ISO 62
Density	1200 / -	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or

Selier represents and warrants exclusively that on the date of delivery by Selier the product shall be in comorming with the specimations agreed upon. Selier his product is a few warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.