

Akulon[®] SG–KGS6

PA66–GF30 FR(40)

30% Glass Fiber Reinforced, Halogen free and free of red phosphorous

Print Date: 2025–10–04

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		DRY / COND	
Molding shrinkage [parallel]	0.2 / *	%	Sim. to ISO 294–4
Molding shrinkage [normal]	0.8 / *	%	Sim. to ISO 294–4
MECHANICAL PROPERTIES		DRY / COND	
Tensile modulus	11000 / 8500	MPa	ISO 527–1/–2
Stress at break	150 / 115	MPa	ISO 527–1/–2
Strain at break	2.8 / 3.2	%	ISO 527–1/–2
Charpy impact strength (+23°C)	63 / –	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	9 / –	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES		DRY / COND	
Melting temperature (10°C/min)	260 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	245 / *	°C	ISO 75–1/–2
Burning Behav. at 1.5 mm nom. thickn.	V–0 / *	class	IEC 60695–11–10
Thickness tested	1.5 / *	mm	IEC 60695–11–10
Burning Behav. at 3.0 mm nom. thickn.	V–0 / *	class	IEC 60695–11–10
Thickness tested	3 / *	mm	IEC 60695–11–10
Burning Behav. at 0.4 mm nom. thickn.	V–0 / *	class	IEC 60695–11–10
Thickness tested	0.4 / *	mm	IEC 60695–11–10
Burning Behav. at 0.75 mm nom. thickn.	V–0 / *	class	IEC 60695–11–10
Thickness tested	0.75 / *	mm	IEC 60695–11–10
Oxygen index	32 / *	%	ISO 4589–1/–2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Akulon[®] SG–KGS6

Print Date: 2025–10–04

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES			
	DRY / COND		
Electric strength	36 / 32	kV/mm	IEC 60243–1
Comparative tracking index	600 / –	V	IEC 60112
OTHER PROPERTIES			
	DRY / COND		
Water absorption	4.3 / *	%	Sim. to ISO 62
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1440 / –	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.