Property Data



Akulon[®] Ultraflow K-FHG6

PA6-GF30

30% Glass Reinforced, Heat Stabilized, High Flow

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	DRY / COND		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	1.1 / *	%	ISO 294-4
MECHANICAL PROPERTIES	DRY / COND		
Tensile modulus	9500 / 5700	MPa	ISO 527-1/-2
Stress at break	175 / 105	MPa	ISO 527-1/-2
Strain at break	3.3 / 7	%	ISO 527-1/-2
Flexural modulus	9000 / 5500	MPa	ISO 178
Flexural strength	270 / 160	MPa	ISO 178
Tensile modulus (200°C)	2650	MPa	ISO 527-1/-2
Stress at break (200°C)	40	MPa	ISO 527-1/-2
Strain at break (200°C)	8.4	%	ISO 527-1/-2
Charpy impact strength (+23°C)	85 / 90	kJ∕m²	ISO 179/1eU
Charpy impact strength (-30°C)	65 / 65	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12.5 / 22	kJ∕m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 10	kJ∕m²	ISO 179/1eA
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7 / *	E-4/°C	ISO 11359-1/-2

Print Date: 2024-10-26

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or

Seller represents and warrants exclusively that on the date of delivery by seller the product shall be in controlling with the opposite table of basis being basis and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied. The products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data Akulon[®] Ultraflow K-FHG6

Density

Print Date: 2024-10-26

ISO 1183

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	3.5 / 14	_	IEC 62631-2-1
Relative permittivity (1 MHz)	3.3 / 5	_	IEC 62631-2-1
Dissipation factor (100 Hz)	50 / 3000	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	150 / 1200	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / 1E12	Ohm*m	IEC 62631-3-1
Surface resistivity	- / 1E13	Ohm	IEC 62631-3-2
Comparative tracking index	* / 450	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	1.8 / *	%	Sim. to ISO 62

1350 / -

kg/m³

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or

Selier represents and warrants exclusively that on the date of delivery by selier the product shall be in comorning with the specifications agreed upon. Selier hakes no other representations or warrants, whether express or implied. Selier is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Selier's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Selier does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.