

Akulon[®] XS36-C1 (FC-X9224)

PA6 copolymer

Very High Viscosity, Lubricated, Film Extrusion, Food Contact Quality

Print Date: 2024-09-17

PA with lower crystallization speed compared to PA6

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MATERIAL SPECIFIC PROPERTIES			
	VALUE		
Viscosity number	245	cm ³ /g	ISO 307, 1157, 1628
RSV formic acid, 1g/100ml	3.6	–	Envalior Method
Melt Viscosity (260 °C)	2250	Pa s	Envalior Method, 260 °C
Density	1130	kg/m ³	ISO 1183
THERMAL PROPERTIES			
	VALUE		
Coeff. of linear therm. expansion (parallel)	0.9	E-4/°C	ISO 11359-1/-2
Spec. heat capacity	1550	J/(kg K)	–
Average spec. heat capacity 20–150 °C	2250	J/(kg K)	–
MECHANICAL PROPERTIES (FILM)			
	VALUE		
Modulus of elasticity	465	MPa	Envalior Method, 50 mm/min
Stress at yield, parallel	34	MPa	ISO 527-3
Maximum stress, parallel	94	MPa	ISO 527-3
Maximum strain, parallel	350	%	ISO 527-3
Trouser Tear resistance, parallel	32	–	ISO 6383-1
Puncture resistance	1320	J/m	Envalior Method
Static coefficient of friction	1.4	–	ISO 8295
Dynamic coefficient of friction	0.8	–	ISO 8295

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data


Akulon[®] XS36-C1 (FC-X9224)

Print Date: 2024-09-17

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
OTHER PROPERTIES (FILM)			
Transparency/Clarity	85	%	Envalior Method
Oxygen transmission rate at 23°C/0%r.h.	23	cm ³ /(m ² *d*bar)	DIS 15105-1/-2
Oxygen transmission rate at 23°C/85%r.h.	33	cm ³ /(m ² *d*bar)	DIS 15105-1/-2
Water Vapor Transmission Rate at 23°C/85%r.h.	35	g/(m ² *d)	DIS 15106-1/-3

TEST SPECIMEN PRODUCTION (FILM)	VALUE		
Type of extrusion	cast	—	—
Thickness of specimen	0.05	mm	—
Extruder temperature	270	°C	
Die temperature	270	°C	
Chill Roll Temperature	110	°C	

Viscosity—shear rate



All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.