

Arnite[®] AV2 370 XL-T

PET-GF35

35% Glass Reinforced, Low Outgassing, Thermal conductive material

Print Date: 2024-09-17

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Molding shrinkage [normal]	0.9	%	Sim. to ISO 294-4
Molding shrinkage [parallel]	0.3	%	Sim. to ISO 294-4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	14000	MPa	ISO 527-1/-2
Stress at break	150	MPa	ISO 527-1/-2
Strain at break	1.5	%	ISO 527-1/-2
Flexural modulus	15000	MPa	ISO 178
Flexural strength	220	MPa	ISO 178
Charpy impact strength (+23°C)	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	7	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	VALUE		
Melting temperature (10°C/min)	255	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	235	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	250	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.25	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.4	E-4/°C	ISO 11359-1/-2
Thermal conductivity in plane	1.6	W/(m K)	ASTM E1461
Thermal conductivity through plane	0.65	W/(m K)	ASTM E1461
ELECTRICAL PROPERTIES			
	VALUE		
Dielectric Constant @ F1	14	-	IEC 60250

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data


Arnite® AV2 370 XL-T

Print Date: 2024-09-17

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Frequency F1	1	GHz	IEC 60250
Volume resistivity	3E11	Ohm*m	IEC 62631-3-1
Electric strength	1.1	kV/mm	IEC 60243-1

OTHER PROPERTIES	VALUE		
Water absorption	0.45	%	Sim. to ISO 62
Humidity absorption	0.18	%	Sim. to ISO 62
Density	1670	kg/m³	ISO 1183

Dielectric Constant – Frequency



All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.