

Arnite[®] B604T

PBT-I

Print Date: 2024-03-27

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	2000	MPa	ISO 527-1/-2
Yield stress	44	MPa	ISO 527-1/-2
Yield strain	3.2	%	ISO 527-1/-2
Nominal strain at break	15	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5.5	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	VALUE		
Temp. of deflection under load (1.80 MPa)	50	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	125	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.95	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.95	E-4/°C	ISO 11359-1/-2
OTHER PROPERTIES			
	VALUE		
Water absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1220	kg/m ³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.