

Arnitel[®] CM550-S

TPC-ES FR

57 Shore D, Extrusion, Flame Retardant

Print Date: 2024-09-17

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume-flow rate	17	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
MECHANICAL PROPERTIES			
	VALUE		
Shore D Hardness (3s)	57	–	ISO 868
Shore D Hardness (15s)	57	–	ISO 868
Tensile modulus	200	MPa	ISO 527-1/-2
Stress at break	28	MPa	ISO 527-1/-2
Nominal strain at break	400	%	ISO 527-1/-2
Stress at 5% strain	10	MPa	ISO 527-1/-2
Stress at 10% strain	14	MPa	ISO 527-1/-2
Stress at 50% strain	18	MPa	ISO 527-1/-2
Stress at 100% strain	17	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	5	kJ/m ²	ISO 179/1eA
Izod notched impact strength (-20°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (-30°C)	5.4	kJ/m ²	ISO 180/1A
Compression Set under constant strain at 70 °C	52	%	ISO 815
MECHANICAL PROPERTIES (DIE CUTTING)			
	VALUE		
Stress at break (normal)	31	MPa	ISO 527-1/-2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Arnitel[®] CM550-S

Print Date: 2024-09-17

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Stress at 5% strain (normal)	9.6	MPa	ISO 527-1/-2
Stress at 10% strain (normal)	13	MPa	ISO 527-1/-2
Stress at 50% strain (normal)	16	MPa	ISO 527-1/-2
Stress at 100% strain (normal)	15	MPa	ISO 527-1/-2
Tear strength (normal)	145	kN/m	ISO 34-1; Method B
Tear strength (parallel)	160	kN/m	ISO 34-1; Method B
Strain at break (normal)	590	%	ISO 527-1/-2

<i>THERMAL PROPERTIES</i>	<i>VALUE</i>		
Melting temperature (10°C/min)	205	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 50N)	71	°C	ISO 306

<i>ELECTRICAL PROPERTIES</i>	<i>VALUE</i>		
Relative permittivity (100Hz)	4.2	–	IEC 62631-2-1
Relative permittivity (1 MHz)	3.5	–	IEC 62631-2-1
Dissipation factor (100 Hz)	180	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	495	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1

<i>OTHER PROPERTIES</i>	<i>VALUE</i>		
Density	1310	kg/m³	ISO 1183
Humidity absorption	0.11	%	Sim. to ISO 62

All the trademarks mentioned here are trademarks of Envalior.
 Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
 Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
 Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
 Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.