

# Arnitel<sup>®</sup> ECO L550

## TPC

34% Renewable Content, Injection Molding, Food Contact Quality

Print Date: 2024-11-07

### Sustainability

Bio-based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>		<b>VALUE</b>	
Melt volume-flow rate	44	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage [parallel]	1.3	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.5	%	Sim. to ISO 294-4
<b>MECHANICAL PROPERTIES</b>		<b>VALUE</b>	
Shore D Hardness (3s)	55	–	ISO 868
Stress at break	27	MPa	ISO 527-1/-2
Nominal strain at break	600	%	ISO 527-1/-2
Stress at 5% strain	8.2	MPa	ISO 527-1/-2
Stress at 10% strain	12.3	MPa	ISO 527-1/-2
Stress at 50% strain	14.7	MPa	ISO 527-1/-2
Stress at 100% strain	13.9	MPa	ISO 527-1/-2
Izod notched impact strength (+23°C)	N	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength (-30°C)	4.2	kJ/m <sup>2</sup>	ISO 180/1A
Tear strength	132	kN/m	ISO 34-1; Method B
Compression Set under constant strain at 70 °C	38	%	ISO 815

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data

# Arnitel<sup>®</sup> ECO L550

Print Date: 2024-11-07

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b>THERMAL PROPERTIES</b>			
	<i>VALUE</i>		
Melting temperature (10°C/min)	196	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 50N)	59	°C	ISO 306
Vicat softening temperature (50°C/h 10N)	156	°C	ISO 306
<b>ELECTRICAL PROPERTIES</b>			
	<i>VALUE</i>		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	20	kV/mm	IEC 60243-1
<b>OTHER PROPERTIES</b>			
	<i>VALUE</i>		
Density	1170	kg/m <sup>3</sup>	ISO 1183
Humidity absorption	0.03	%	Sim. to ISO 62

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.