

# Arnitel<sup>®</sup> EL150

## TPC-ET

Injection Molding

Print Date: 2025-10-04

Arnitel EL150 is a very low modulus grade with nominal hardness of 20D. Material can be processed by many conventional thermoplastics processing techniques such as injection molding. It is important to note that in a certain periods, clumps can be formed due to excessive storage conditions such as packing type, stacking, extreme temperature. Pl. refer injection molding recommendations

Food contact use – Not Applicable.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>		VALUE	
Melt volume–flow rate	76	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage [parallel]	0.7	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1	%	Sim. to ISO 294-4
<b>MECHANICAL PROPERTIES</b>		VALUE	
Shore D Hardness (3s)	19	–	ISO 868
Shore D Hardness (15s)	18	–	ISO 868
Shore A Hardness (3s)	80	–	ISO 868
Shore A Hardness (15s)	79	–	ISO 868
Tensile modulus	16	MPa	ISO 527-1/-2
Stress at break	14.4	MPa	ISO 527-1/-2
Nominal strain at break	980	%	ISO 527-1/-2
Stress at 5% strain	0.8	MPa	ISO 527-1/-2
Stress at 10% strain	1.4	MPa	ISO 527-1/-2
Stress at 50% strain	3.1	MPa	ISO 527-1/-2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Arnitel<sup>®</sup> EL150

Print Date: 2025-10-04

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Stress at 100% strain	3.8	MPa	ISO 527-1/-2
THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	165	°C	ISO 11357-1/-3
OTHER PROPERTIES	VALUE		
Density	1060	kg/m³	ISO 1183
Humidity absorption	0.12	%	Sim. to ISO 62

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalor 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalor.