

Arnitel[®] EM400 B–MB

TPC–ET

Injection Molding, Film Extrusion, Food Contact Quality

Print Date: 2026–04–09

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume–flow rate (MVR)	33	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage [parallel]	1.5	%	Sim. to ISO 294–4
Molding shrinkage [normal]	1.5	%	Sim. to ISO 294–4

MECHANICAL PROPERTIES			
	VALUE		
Shore D Hardness (3s)	33	–	ISO 868
Tensile modulus	40	MPa	ISO 527–1/–2
Stress at break	20	MPa	ISO 527–1/–2
Nominal strain at break	830	%	ISO 527–1/–2
Stress at 5% strain	2.3	MPa	ISO 527–1/–2
Stress at 10% strain	3.8	MPa	ISO 527–1/–2
Stress at 50% strain	6.8	MPa	ISO 527–1/–2
Stress at 100% strain	7.5	MPa	ISO 527–1/–2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	N	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (–20°C)	N	kJ/m ²	ISO 180/1A
Flexural modulus	50	MPa	ISO 178

MECHANICAL PROPERTIES (DIE CUTTING) VALUE

Arnitel[®] EM400 B–MB

Print Date: 2026–04–09

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Stress at break (normal)	19	MPa	ISO 527–1/–2
Tear strength (normal)	104	kN/m	ISO 34–1; Method B
Tear strength (parallel)	106	kN/m	ISO 34–1; Method B
Strain at break (normal)	960	%	ISO 527–1/–2
<i>THERMAL PROPERTIES</i>		<i>VALUE</i>	
Melting temperature (10°C/min)	195	°C	ISO 11357–1/–3
Coeff. of linear therm. expansion (parallel)	2.2	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	2.2	E–4/°C	ISO 11359–1/–2
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	1.5	mm	IEC 60695–11–10
<i>ELECTRICAL PROPERTIES</i>		<i>VALUE</i>	
Relative permittivity (100Hz)	4.1	–	IEC 62631–2–1
Relative permittivity (1 MHz)	4	–	IEC 62631–2–1
Dissipation factor (100 Hz)	10	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	170	E–4	IEC 62631–2–1
Volume resistivity	1E13	Ohm*m	IEC 62631–3–1
Electric strength	20	kV/mm	IEC 60243–1
Comparative tracking index	600	V	IEC 60112
<i>OTHER PROPERTIES</i>		<i>VALUE</i>	
Density	1110	kg/m ³	ISO 1183
Apparent density	690	kg/m ³	ISO 60
Water absorption	0.75	%	Sim. to ISO 62
Humidity absorption	0.3	%	Sim. to ISO 62