

# Arnitel<sup>®</sup> PB500-H

## TPC-ET

Blow Molding Grade, Heat Stabilized

Print Date: 2024-06-20

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	VALUE		
Melt volume-flow rate	2	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	10	kg	ISO 1133
Molding shrinkage (parallel)	1.7	%	ISO 294-4
Molding shrinkage (normal)	1.8	%	ISO 294-4
<b>MECHANICAL PROPERTIES</b>			
	VALUE		
Shore D Hardness (3s)	50	—	ISO 868
Shore A Hardness (3s)	94	—	ISO 868
Tensile modulus	175	MPa	ISO 527-1/-2
Stress at break	27	MPa	ISO 527-1/-2
Nominal strain at break	150	%	ISO 527-1/-2
Stress at 5% strain	9.4	MPa	ISO 527-1/-2
Stress at 10% strain	14	MPa	ISO 527-1/-2
Stress at 50% strain	22	MPa	ISO 527-1/-2
Stress at 100% strain	26	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	14	kJ/m <sup>2</sup>	ISO 179/1eA
<b>MECHANICAL PROPERTIES (DIE CUTTING)</b>			
	VALUE		
Stress at break (normal)	36	MPa	ISO 527-1/-2
Stress at 5% strain (normal)	8.5	MPa	ISO 527-1/-2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data

# Arnitel<sup>®</sup> PB500-H

Print Date: 2024-06-20

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Stress at 10% strain (normal)	11	MPa	ISO 527-1/-2
Stress at 50% strain (normal)	14	MPa	ISO 527-1/-2
Stress at 100% strain (normal)	15	MPa	ISO 527-1/-2
Strain at break (normal)	640	%	ISO 527-1/-2
Stress at 10% strain (parallel)	9	MPa	ISO 527-1/-2
Stress at 10% strain (parallel) (+100°C)	4.6	MPa	ISO 527-1/-2
Tear strength (normal)	116	kN/m	ISO 34-1; Method B
Tear strength (parallel)	121	kN/m	ISO 34-1; Method B

<i>THERMAL PROPERTIES</i>	<i>VALUE</i>		
Melting temperature (10°C/min)	202	°C	ISO 11357-1/-3
Temp. of deflection under load (0.45 MPa)	63	°C	ISO 75-1/-2

<i>OTHER PROPERTIES</i>	<i>VALUE</i>		
Density	1220	kg/m <sup>3</sup>	ISO 1183
Humidity absorption	0.5	%	Sim. to ISO 62

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.