

Arnitel[®] PL381

TPC-ET

Injection Molding

Print Date: 2024-09-17

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume-flow rate	32	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (parallel)	1.55	%	ISO 294-4
Molding shrinkage (normal)	1.75	%	ISO 294-4
MECHANICAL PROPERTIES			
	VALUE		
Shore D Hardness (3s)	33	—	ISO 868
Tensile modulus	45	MPa	ISO 527-1/-2
Stress at break	14	MPa	ISO 527-1/-2
Nominal strain at break	450	%	ISO 527-1/-2
Stress at 5% strain	2.5	MPa	ISO 527-1/-2
Stress at 10% strain	4	MPa	ISO 527-1/-2
Stress at 50% strain	7	MPa	ISO 527-1/-2
Stress at 100% strain	8.5	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	N	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (-20°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (-30°C)	N	kJ/m ²	ISO 180/1A
Tear strength	74	kN/m	ISO 34-1; Method B

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Arnitel[®] PL381

Print Date: 2024-09-17

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
THERMAL PROPERTIES			
	VALUE		
Melting temperature (10°C/min)	212	°C	ISO 11357-1/-3
Coeff. of linear therm. expansion (parallel)	1.5	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.5	E-4/°C	ISO 11359-1/-2
ELECTRICAL PROPERTIES			
	VALUE		
Relative permittivity (100Hz)	4.7	—	IEC 62631-2-1
Relative permittivity (1 MHz)	4.4	—	IEC 62631-2-1
Dissipation factor (100 Hz)	310	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	810	E-4	IEC 62631-2-1
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Electric strength	20	kV/mm	IEC 60243-1
Comparative tracking index	600	V	IEC 60112
OTHER PROPERTIES			
	VALUE		
Density	1160	kg/m ³	ISO 1183
Water absorption	7	%	Sim. to ISO 62
Humidity absorption	0.4	%	Sim. to ISO 62

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.