


Caprolactam

CAS RN: 105–60–2

Print Date: 2026–04–09

Applications

Caprolactam is used for the production of fibers and filaments made of polyamide 6. Examples for end products of polyamide 6 are: clothing, carpets, ropes, fishing nets, molded plastic parts and packaging films. Engineering plastics like Durethan or cast nylon (shaped as sheet, plates, pipes, cast or rotational molded parts) are another important market for caprolactam. It is also used in numerous special applications.



Storage and shelf life

Caprolactam is a very stable product and it does not lose its properties even after a long period of storage. There is no limiting shelf life, it can be stored for several weeks or months, provided it is stored as follows:

Liquid

Store in suitable tanks or containers from stainless steel or aluminum. All the elements of the storage and conveying systems must be grounded. Store in well isolated and tempered tanks or containers under nitrogen blanket. Ensure adequate ventilation or aspiration when handling or transferring the product.

Solid

Store in a cool, dry place and protected from moisture. Dust may explode and therefore must be removed by effective ventilation. Bags must not be damaged and should be kept closed. After partly use – which is not recommended – bags shall be resealed. It tends to agglomerate (caking) after longer transport and storage (vibrations and recurring temperature changes). This can be fixed by applying e.g. light impacts against the closed bag. Caking does not affect the chemical properties of the product.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Caprolactam

Print Date: 2026-04-09

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
CHARACTERISTICS			
Crystallization point	≥ 69	°C	based on ISO 7060
Moisture	≤ 0.04	wt-%	KF titration
(use in anionic polymerization)	≤ 0.01	wt-%	KF titration
Volatile bases	≤ 0.5	meq/kg	based on ISO 8661
Permanganate number	≥ 10,000	s	Spectrophotom. (3% solution)
Color of 50 wt-% aqueous solution	≤ 5	APHA	based on ISO 8112
Content of free bases	≤ 0.1	meq/kg	Titration
Content of free acids	≤ 0.05	meq/kg	Titration
Absorbance at 290 nm	≤ 0.05		based on ISO 7059
Cyclohexanone oxime content	≤ 5	mg/kg	GC
Iron content	≤ 0.5	mg/kg	Spectrophotom.
Ash	≤ 10	mg/kg	TGA
PACKAGING			
Bag (solid product)	25	kg	
Pallet (40 bags)	1000	kg	
Dimensions	1,000 x 1,130 x 1,000	mm ³	
Pallet (50 bags)	1250	kg	
Dimensions	1,400 x 1,130 x 1,380	mm ³	
Tank (liquid product)	25 to 31	t	

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.