

# Durethan® B31SKH3.0LT

## PA6

Injection Molding, Unreinforced, Heat Stabilized, Laser Transparent Black

Print Date: 2024-09-17

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		DRY / COND	
Molding shrinkage (parallel)	1 / *	%	ISO 294-4
Molding shrinkage (normal)	1.1 / *	%	ISO 294-4
MECHANICAL PROPERTIES		DRY / COND	
Tensile modulus	3500 / 1000	MPa	ISO 527-1/-2
Nominal strain at break	10 / >50	%	ISO 527-1/-2
Yield stress	80 / 45	MPa	ISO 527-1/-2
Yield strain	4 / 20	%	ISO 527-1/-2
Flexural modulus	2900 / 900	MPa	ISO 178
Flexural strength	115 / 35	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	<10 / 25	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	<10 / <10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	<10 / 20	kJ/m²	ISO 180/1A
THERMAL PROPERTIES		DRY / COND	
Melting temperature (10°C/min)	221 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	60 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	170 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.8 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2

All the trademarks mentioned here are trademarks of Envalior.  
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Durethan® B31SKH3.0LT

Print Date: 2024-09-17

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES			
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
OTHER PROPERTIES			
Water absorption	10 / *	%	Sim. to ISO 62
Humidity absorption	3 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS			
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2-6	h	
Residual moisture content	0.03-0.12	%	acc. to Karl Fischer
Melt temperature (Tmin - Tmax)	260-280	°C	
Mold temperature	80-100	°C	

All the trademarks mentioned here are trademarks of Envalior.  
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.