

# Durethan<sup>®</sup> ECOBKV25F30

## PA6—GF25 FR(17)

25% Glass Fiber Reinforced, Injection Molding, Heat Stabilized, Recycled Content

Print Date: 2025–10–14

### Sustainability

Mass balanced  
Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>	<b>DRY / COND</b>		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294–4
Molding shrinkage (normal)	0.6 / *	%	ISO 294–4
<b>MECHANICAL PROPERTIES</b>	<b>DRY / COND</b>		
Tensile modulus	11000 / 7300	MPa	ISO 527–1/–2
Stress at break	150 / 90	MPa	ISO 527–1/–2
Strain at break	2.3 / 4.4	%	ISO 527–1/–2
Flexural modulus	10000 / 7000	MPa	ISO 178
Flexural strength	230 / 155	MPa	ISO 178
Charpy impact strength (+23°C)	55 / 55	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (–30°C)	45 / 50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 15	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (–30°C)	<10 / <10	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength (+23°C)	10 / 15	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL PROPERTIES</b>	<b>DRY / COND</b>		
Melting temperature (10°C/min)	222 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	205 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E–4/°C	ISO 11359–1/–2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Durethan® ECOBKV25F30

Print Date: 2025-10-14

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Coeff. of linear therm. expansion (normal)	0.9 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Burning Behav. at 0.4 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.4 / -	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	0.75 / -	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	850 / -	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	0.4 / -	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	850 / -	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	0.75 / -	mm	IEC 60695-2-13
ELECTRICAL PROPERTIES		DRY / COND	
Volume resistivity	3.4E12 / -	Ohm*m	IEC 62631-3-1
Comparative tracking index	400 / -	V	IEC 60112
OTHER PROPERTIES		DRY / COND	
Water absorption	4.3 / *	%	Sim. to ISO 62
Humidity absorption	1.3 / *	%	Sim. to ISO 62
Density	1600 / -	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS		VALUE	
Drying temperature dry air dryer	80	°C	

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Durethan® ECOBKV25F30

Print Date: 2025-10-14

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Drying time dry air dryer	2-6	h	
Residual moisture content	0.03-0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	270-290	°C	
Mold temperature	80-100	°C	

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.