

Durethan® ECOBKV35H2.0

PA6—GF35

35% Glass Fiber Reinforced, Injection Molding, Heat Stabilized, Recycled Content

Print Date: 2025–10–14

Sustainability

Mass balanced
Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		DRY / COND	
Molding shrinkage (parallel)	0.25 / *	%	ISO 294–4
Molding shrinkage (normal)	0.7 / *	%	ISO 294–4
MECHANICAL PROPERTIES		DRY / COND	
Tensile modulus	11000 / 6500	MPa	ISO 527–1/–2
Stress at break	185 / 110	MPa	ISO 527–1/–2
Strain at break	3.3 / 6.5	%	ISO 527–1/–2
Flexural modulus	10500 / 6200	MPa	ISO 178
Flexural strength	290 / 180	MPa	ISO 178
Tensile modulus (200°C)	3390	MPa	ISO 527–1/–2
Charpy impact strength (+23°C)	90 / 100	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	75 / 70	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 20	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	<10 / 10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	15 / 20	kJ/m²	ISO 180/1A
THERMAL PROPERTIES		DRY / COND	
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	205 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75–1/–2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Durethan® ECOBKV35H2.0

Print Date: 2025-10-14

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.95 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Oxygen index	23 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	650 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2 / -	mm	IEC 60695-2-12
ELECTRICAL PROPERTIES		DRY / COND	
Comparative tracking index	475 / -	V	IEC 60112
OTHER PROPERTIES		DRY / COND	
Water absorption	6.5 / *	%	Sim. to ISO 62
Humidity absorption	1.9 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES		DRY / COND	
Viscosity number	140 / *	cm³/g	ISO 307, 1157, 1628
PROCESSING RECOMMENDATIONS		VALUE	
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2-6	h	
Residual moisture content	0.03-0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	270-290	°C	
Mold temperature	80-120	°C	

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.