

EcoPaXX[®] Q–DWX10

PA410–GF50

50% Glass Fiber Reinforced, Excellent Surface Properties, Drinking Water Grade, Food Contact Quality

Print Date: 2025–10–09

EcoPaXX[®] Q–DWX10 is a long aliphatic polyamide with excellent mechanical & flow performance for use in food contact & drinking water applications

Sustainability

Bio–based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.13 / *	%	ISO 294–4
Molding shrinkage (normal)	0.73 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	16500 / 16000	MPa	ISO 527–1/–2
Stress at break	240 / 210	MPa	ISO 527–1/–2
Strain at break	3 / 3.3	%	ISO 527–1/–2
Tensile modulus (80°C)	12000 / –	MPa	ISO 527–1/–2
Stress at break (80°C)	140 / –	MPa	ISO 527–1/–2
Strain at break (80°C)	5.5 / –	%	ISO 527–1/–2
Tensile modulus (120°C)	4900 / –	MPa	ISO 527–1/–2
Stress at break (120°C)	75 / –	MPa	ISO 527–1/–2
Strain at break (120°C)	12 / –	%	ISO 527–1/–2
Tensile modulus (140°C)	4500	MPa	ISO 527–1/–2
Stress at break (140°C)	60	MPa	ISO 527–1/–2
Strain at break (140°C)	11	%	ISO 527–1/–2
Tensile modulus (160°C)	4000	MPa	ISO 527–1/–2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

EcoPaXX® Q–DWX10

Print Date: 2025–10–09

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Stress at break (160°C)	50	MPa	ISO 527–1/–2
Strain at break (160°C)	10	%	ISO 527–1/–2
Charpy impact strength (+23°C)	100 / 80	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	90 / 75	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	16 / 13	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	14 / 13	kJ/m²	ISO 179/1eA
Flexural modulus	15500 / 15000	MPa	ISO 178
Flexural strength	380 / 330	MPa	ISO 178

THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	250 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	235 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.16 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.6 / *	E–4/°C	ISO 11359–1/–2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695–11–10
Thickness tested	1.5 / *	mm	IEC 60695–11–10
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695–11–10
Thickness tested	3 / *	mm	IEC 60695–11–10
Glow Wire Flammability Index GWFI	900 / –	°C	IEC 60695–2–12
GWFI (Thickness (1) tested)	3 / –	mm	IEC 60695–2–12
Glow Wire Flammability Index GWFI	700 / –	°C	IEC 60695–2–12
GWFI (Thickness (2) tested)	1.5 / –	mm	IEC 60695–2–12
Glow Wire Ignition Temperature GWIT	750 / –	°C	IEC 60695–2–13
GWIT (Thickness (1) tested)	3 / –	mm	IEC 60695–2–13
Glow Wire Ignition Temperature GWIT	725 / –	°C	IEC 60695–2–13
GWIT (Thickness (2) tested)	1.5 / –	mm	IEC 60695–2–13

ELECTRICAL PROPERTIES DRY / COND

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

EcoPaXX[®] Q–DWX10

Print Date: 2025–10–09

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Electric strength	27 / –	kV/mm	IEC 60243–1
OTHER PROPERTIES	DRY / COND		
Water absorption	3 / *	%	Sim. to ISO 62
Humidity absorption	1.2 / *	%	Sim. to ISO 62
Density	1570 / –	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.