

ForTii[®] Ace JTX8

PPA–GF30

30% Glass Fiber Reinforced, PA4T, Electro–friendly, Improved resistance to blistering during reflow – soldering process, Improved color stability

Print Date: 2026–01–14

ForTii[®] Ace JTX8 is the only polyamide grade in the world that secures, in all product designs, the JEDEC MSL 1 rating at all thicknesses. Ace JTX8 has the highest Tg available in polyamides (160°C) to satisfy various industry requirements like chemical resistance and high temperature thermal ageing. Ace JTX8 has extremely robust processing performance and allows 100% regrinding with high mechanical properties retention.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.43 / *	%	ISO 294–4
Molding shrinkage (normal)	1.2 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	11000 / 11000	MPa	ISO 527–1/–2
Tensile modulus (–40°C)	11700 / –	MPa	ISO 527–1/–2
Tensile modulus (40°C)	10500 / –	MPa	ISO 527–1/–2
Tensile modulus (80°C)	10300 / 9500	MPa	ISO 527–1/–2
Tensile modulus (100°C)	10200 / –	MPa	ISO 527–1/–2
Tensile modulus (120°C)	9500 / –	MPa	ISO 527–1/–2
Tensile modulus (160°C)	6000	MPa	ISO 527–1/–2
Tensile modulus (200°C)	4000	MPa	ISO 527–1/–2
Stress at break	210 / 190	MPa	ISO 527–1/–2
Stress at break (–40°C)	240 / –	MPa	ISO 527–1/–2
Stress at break (40°C)	200 / –	MPa	ISO 527–1/–2
Stress at break (80°C)	180 / 120	MPa	ISO 527–1/–2
Stress at break (100°C)	170 / –	MPa	ISO 527–1/–2
Stress at break (120°C)	150 / –	MPa	ISO 527–1/–2
Stress at break (160°C)	100	MPa	ISO 527–1/–2
Stress at break (200°C)	75	MPa	ISO 527–1/–2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

ForTii[®] Ace JTX8

Print Date: 2026-01-14

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Strain at break	2.7 / 2.5	%	ISO 527-1/-2
Strain at break (-40°C)	2.8 / -	%	ISO 527-1/-2
Strain at break (40°C)	2.6 / -	%	ISO 527-1/-2
Strain at break (80°C)	2.8 / 3	%	ISO 527-1/-2
Strain at break (100°C)	2.7 / -	%	ISO 527-1/-2
Strain at break (120°C)	3 / -	%	ISO 527-1/-2
Strain at break (160°C)	5	%	ISO 527-1/-2
Strain at break (200°C)	6	%	ISO 527-1/-2
Flexural modulus	10500 / 10500	MPa	ISO 178
Flexural strength	300 / 275	MPa	ISO 178
Flexural modulus (120°C)	9500	MPa	ISO 178
Flexural modulus (160°C)	5700	MPa	ISO 178
Flexural modulus (200°C)	3900	MPa	ISO 178
Charpy impact strength (+23°C)	70 / 60	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	65 / 55	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 8	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 8	kJ/m ²	ISO 179/1eA
<i>THERMAL PROPERTIES</i>		<i>DRY / COND</i>	
Melting temperature (10°C/min)	340 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	320 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.18 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	HB / *	mm	IEC 60695-11-10
UL recognition	3 / *	-	-
Thermal Index 5000 hrs	174	°C	IEC 60216/ISO 527-1/-2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

ForTii[®] Ace JTX8

Print Date: 2026-01-14

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>ELECTRICAL PROPERTIES</i>			
Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 62631-3-1
Electric strength	45 / 40	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	V	IEC 60112
Relative permittivity (1GHz)	3.92 / 3.88	-	IEC 61189-2-721
Relative permittivity (10GHz)	3.83 / -	-	IEC 61189-2-721
<i>OTHER PROPERTIES</i>			
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1460 / -	kg/m ³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.