

# ForTii<sup>®</sup> Ace MX53B

## PPA–GF50

50% Glass Reinforced, PA4T, Heat Stabilized, for Structural Parts

Print Date: 2024–09–20

ForTii<sup>®</sup> Ace MX53B is a high Tg PPA combining good toughness at low temperatures and chemical resistance. It is designed to replace metal in structural parts that need high performance over a broad temperature range, from –35°C to above 150°C, both in dry as well as conditioned environment.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Molding shrinkage (parallel)	0.33 / *	%	ISO 294–4
Molding shrinkage (normal)	0.85 / *	%	ISO 294–4
<b>MECHANICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Tensile modulus	18000 / 18900	MPa	ISO 527–1/–2
Tensile modulus (–40°C)	19000 / 19200	MPa	ISO 527–1/–2
Tensile modulus (40°C)	17500 / 18000	MPa	ISO 527–1/–2
Tensile modulus (80°C)	17000 / 14000	MPa	ISO 527–1/–2
Tensile modulus (100°C)	16800 / 8800	MPa	ISO 527–1/–2
Tensile modulus (120°C)	16000 / 7300	MPa	ISO 527–1/–2
Tensile modulus (150°C)	9000	MPa	ISO 527–1/–2
Tensile modulus (160°C)	7700	MPa	ISO 527–1/–2
Tensile modulus (180°C)	6200	MPa	ISO 527–1/–2
Tensile modulus (200°C)	5800	MPa	ISO 527–1/–2
Stress at break	260 / 240	MPa	ISO 527–1/–2
Stress at break (–40°C)	320 / 290	MPa	ISO 527–1/–2
Stress at break (40°C)	245 / 220	MPa	ISO 527–1/–2
Stress at break (80°C)	205 / 140	MPa	ISO 527–1/–2
Stress at break (100°C)	195 / 105	MPa	ISO 527–1/–2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

ForTii<sup>®</sup> Ace MX53B

Print Date: 2024-09-20

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Stress at break (120°C)	170 / 85	MPa	ISO 527-1/-2
Stress at break (150°C)	100	MPa	ISO 527-1/-2
Stress at break (160°C)	96	MPa	ISO 527-1/-2
Stress at break (180°C)	75	MPa	ISO 527-1/-2
Stress at break (200°C)	65	MPa	ISO 527-1/-2
Strain at break	2.1 / 2	%	ISO 527-1/-2
Strain at break (-40°C)	2.3 / 2	%	ISO 527-1/-2
Strain at break (40°C)	2.1 / 1.9	%	ISO 527-1/-2
Strain at break (80°C)	2.2 / 3.2	%	ISO 527-1/-2
Strain at break (100°C)	2.3 / 4.2	%	ISO 527-1/-2
Strain at break (120°C)	2.4 / 4.8	%	ISO 527-1/-2
Strain at break (150°C)	5	%	ISO 527-1/-2
Strain at break (160°C)	6	%	ISO 527-1/-2
Strain at break (180°C)	6	%	ISO 527-1/-2
Strain at break (200°C)	6	%	ISO 527-1/-2
Flexural modulus	17800 / 18000	MPa	ISO 178
Flexural strength	390 / 350	MPa	ISO 178
Flexural modulus (120°C)	16300	MPa	ISO 178
Flexural modulus (160°C)	8500	MPa	ISO 178
Flexural modulus (180°C)	6700	MPa	ISO 178
Flexural modulus (200°C)	6200	MPa	ISO 178
Charpy impact strength (+23°C)	80 / 70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	75 / 65	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / 9.5	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	11 / 9.5	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL PROPERTIES</b>		<b>DRY / COND</b>	
Melting temperature (10°C/min)	330 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	305 / *	°C	ISO 75-1/-2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data (Provisional)

# ForTii<sup>®</sup> Ace MX53B

Print Date: 2024-09-20

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Coeff. of linear therm. expansion (parallel)	0.14 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.47 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (parallel)	0.27	E-4/°C	ASTM D696
Coeff. of linear therm. expansion (normal)	0.3	E-4/°C	ASTM D696
Thermal Index 5000 hrs	178	°C	IEC 60216/ISO 527-1/-2

### *ELECTRICAL PROPERTIES*

#### *DRY / COND*

Comparative tracking index	400 / -	V	IEC 60112
----------------------------	---------	---	-----------

### *OTHER PROPERTIES*

#### *DRY / COND*

Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1660 / -	kg/m <sup>3</sup>	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.