

ForTii[®] Ace MX54B

PPA—GF60

60% Glass Reinforced, PA4T, Heat Stabilized, for Structural Parts

Print Date: 2024-03-27

ForTii[®] Ace MX54B is a high Tg PPA combining good toughness at low temperatures and chemical resistance. It is designed to have a dimensional stability close to aluminum. It has a high mechanical performance over a broad temperature range, from -35°C to above 150°C, both in dry as well as conditioned environment.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.4 / *	%	ISO 294-4
Molding shrinkage (normal)	0.8 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	23000 / 23800	MPa	ISO 527-1/-2
Tensile modulus (-40°C)	25000 / 24000	MPa	ISO 527-1/-2
Tensile modulus (40°C)	22500 / 23500	MPa	ISO 527-1/-2
Tensile modulus (80°C)	22000 / 17800	MPa	ISO 527-1/-2
Tensile modulus (100°C)	21500 / 10900	MPa	ISO 527-1/-2
Tensile modulus (120°C)	20500 / 9500	MPa	ISO 527-1/-2
Tensile modulus (150°C)	12500	MPa	ISO 527-1/-2
Tensile modulus (160°C)	9800	MPa	ISO 527-1/-2
Tensile modulus (180°C)	8100	MPa	ISO 527-1/-2
Tensile modulus (200°C)	7400	MPa	ISO 527-1/-2
Stress at break	270 / 250	MPa	ISO 527-1/-2
Stress at break (-40°C)	330 / 320	MPa	ISO 527-1/-2
Stress at break (40°C)	260 / 230	MPa	ISO 527-1/-2
Stress at break (80°C)	230 / 140	MPa	ISO 527-1/-2
Stress at break (100°C)	210 / 100	MPa	ISO 527-1/-2
Stress at break (120°C)	180 / 80	MPa	ISO 527-1/-2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

ForTii[®] Ace MX54B

Print Date: 2024-03-27

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Stress at break (150°C)	115	MPa	ISO 527-1/-2
Stress at break (160°C)	95	MPa	ISO 527-1/-2
Stress at break (180°C)	75	MPa	ISO 527-1/-2
Stress at break (200°C)	65	MPa	ISO 527-1/-2
Strain at break	1.8 / 1.85	%	ISO 527-1/-2
Strain at break (-40°C)	1.8 / 1.75	%	ISO 527-1/-2
Strain at break (40°C)	1.75 / 1.65	%	ISO 527-1/-2
Strain at break (80°C)	1.8 / 2.6	%	ISO 527-1/-2
Strain at break (100°C)	1.8 / 3	%	ISO 527-1/-2
Strain at break (120°C)	1.9 / 3.3	%	ISO 527-1/-2
Strain at break (150°C)	3.5	%	ISO 527-1/-2
Strain at break (160°C)	4	%	ISO 527-1/-2
Strain at break (180°C)	4	%	ISO 527-1/-2
Strain at break (200°C)	4	%	ISO 527-1/-2
Flexural modulus	23500 / 24000	MPa	ISO 178
Flexural strength	420 / 390	MPa	ISO 178
Flexural modulus (120°C)	20000	MPa	ISO 178
Flexural modulus (160°C)	12000	MPa	ISO 178
Flexural modulus (180°C)	9000	MPa	ISO 178
Flexural modulus (200°C)	8200	MPa	ISO 178
Charpy impact strength (+23°C)	90 / 75	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	75 / 75	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	13 / 11	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	13 / 12	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES		DRY / COND	
Melting temperature (10°C/min)	330 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	307 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.13 / *	E-4/°C	ISO 11359-1/-2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data (Provisional)

ForTii[®] Ace MX54B

Print Date: 2024-03-27

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Coeff. of linear therm. expansion (normal)	0.41 / *	E-4/°C	ISO 11359-1/-2
Thermal Index 5000 hrs	176	°C	IEC 60216/ISO 527-1/-2
<i>ELECTRICAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Comparative tracking index	425 / -	V	IEC 60112
<i>OTHER PROPERTIES</i>			
	<i>DRY / COND</i>		
Humidity absorption	1.2 / *	%	Sim. to ISO 62
Density	1780 / -	kg/m ³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.