

ForTii[®] Ace WX51–FC

PPA–GF30

30% Glass Fiber Reinforced, PA4T, Food Contact Quality, Drinking Water Grade

Print Date: 2025–08–21

ForTii[®] Ace WX51–FC has best in class high temperature and wet mechanical performance, weldline strength and weldline strength retention in hot water and steam. For detailed statements and information regarding food contact and water contact approvals please contact your Envalior representative.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.43 / *	%	ISO 294–4
Molding shrinkage (normal)	1.2 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	11000 / 11000	MPa	ISO 527–1/–2
Tensile modulus (–40°C)	11800 / –	MPa	ISO 527–1/–2
Tensile modulus (40°C)	10500 / –	MPa	ISO 527–1/–2
Tensile modulus (80°C)	10300 / 9500	MPa	ISO 527–1/–2
Tensile modulus (100°C)	10200 / –	MPa	ISO 527–1/–2
Tensile modulus (120°C)	9600 / 5500	MPa	ISO 527–1/–2
Tensile modulus (150°C)	7500	MPa	ISO 527–1/–2
Tensile modulus (160°C)	6300	MPa	ISO 527–1/–2
Tensile modulus (180°C)	4900	MPa	ISO 527–1/–2
Tensile modulus (200°C)	4400	MPa	ISO 527–1/–2
Stress at break	210 / 190	MPa	ISO 527–1/–2
Stress at break (–40°C)	240 / –	MPa	ISO 527–1/–2
Stress at break (40°C)	200 / –	MPa	ISO 527–1/–2
Stress at break (80°C)	180 / 120	MPa	ISO 527–1/–2
Stress at break (100°C)	170 / –	MPa	ISO 527–1/–2
Stress at break (120°C)	150 / 80	MPa	ISO 527–1/–2
Stress at break (150°C)	115	MPa	ISO 527–1/–2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

ForTii[®] Ace WX51–FC

Print Date: 2025–08–21

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Stress at break (160°C)	100	MPa	ISO 527–1/–2
Stress at break (200°C)	75	MPa	ISO 527–1/–2
Strain at break	2.6 / 2.5	%	ISO 527–1/–2
Strain at break (–40°C)	2.7 / –	%	ISO 527–1/–2
Strain at break (40°C)	2.5 / –	%	ISO 527–1/–2
Strain at break (80°C)	2.7 / 2.8	%	ISO 527–1/–2
Strain at break (100°C)	2.7 / –	%	ISO 527–1/–2
Strain at break (120°C)	3 / 5	%	ISO 527–1/–2
Strain at break (150°C)	3.8	%	ISO 527–1/–2
Strain at break (160°C)	5	%	ISO 527–1/–2
Strain at break (180°C)	5	%	ISO 527–1/–2
Strain at break (200°C)	5	%	ISO 527–1/–2
Flexural modulus	10500 / 10500	MPa	ISO 178
Flexural strength	300 / 275	MPa	ISO 178
Flexural modulus (120°C)	9500	MPa	ISO 178
Flexural modulus (160°C)	5700	MPa	ISO 178
Flexural modulus (180°C)	4700	MPa	ISO 178
Flexural modulus (200°C)	4300	MPa	ISO 178
Charpy impact strength (+23°C)	70 / 60	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	65 / 55	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 8	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	10 / 8	kJ/m²	ISO 179/1eA

THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	340 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	320 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.18 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.6 / *	E–4/°C	ISO 11359–1/–2
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695–11–10

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

ForTii[®] Ace WX51–FC

Print Date: 2025–08–21

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Thickness tested	HB / *	mm	IEC 60695–11–10
UL recognition	3 / *	–	–
ELECTRICAL PROPERTIES	DRY / COND		
Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 62631–3–1
Electric strength	45 / –	kV/mm	IEC 60243–1
Comparative tracking index	600 / –	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1460 / –	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.