

ForTii[®] K12

PPA–GF40

40% Glass Fiber Reinforced, PA4T, Electro–friendly

Print Date: 2026–04–09

ForTii[®] K12 combines high mechanical strength and good flowability, ideal for designs requiring dimensional stability and impact resistance. K12 is suitable for applications such as sensor housing or camera bracket.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.35 / *	%	ISO 294–4
Molding shrinkage (normal)	1 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	13500 / –	MPa	ISO 527–1/–2
Stress at break	210 / –	MPa	ISO 527–1/–2
Strain at break	2 / –	%	ISO 527–1/–2
Flexural modulus	13500 / –	MPa	ISO 178
Flexural strength	330 / –	MPa	ISO 178
Charpy impact strength (+23°C)	65 / –	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / –	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	325 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	305 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.16 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.53 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (parallel)	0.3	E–4/°C	ASTM D696
Coeff. of linear therm. expansion (normal)	0.4	E–4/°C	ASTM D696
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695–11–10

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

ForTii[®] K12

Print Date: 2026-04-09

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Thickness tested	HB / *	mm	IEC 60695-11-10
UL recognition	3 / *	–	–
<i>ELECTRICAL PROPERTIES</i>	<i>DRY / COND</i>		
Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 62631-3-1
Electric strength	33 / 33	kV/mm	IEC 60243-1
Comparative tracking index	600 / –	V	IEC 60112
Relative permittivity (100Hz)	5 / 5	–	IEC 62631-2-1
Relative permittivity (1 MHz)	4.5 / 4.5	–	IEC 62631-2-1
<i>OTHER PROPERTIES</i>	<i>DRY / COND</i>		
Humidity absorption	1.7 / *	%	Sim. to ISO 62
Density	1530 / –	kg/m ³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.