

# ForTii<sup>®</sup> LDS51B

## PPA—GF30 FR(40)

30% Glass Reinforced, PA4T, Halogen free and free of red phosphorous, Certified V-0 at 0.4mm, Laser Direct Structuring (LDS)

Print Date: 2024-03-27

ForTii<sup>®</sup> LDS51B is a truly reflow compatible and halogen-free flame retardancy grade. LDS51B has superior plating performance and is compatible with a broad range of laser settings enabling high resolution and fine line capability.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
DRY / COND			
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	1 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
DRY / COND			
Tensile modulus	11500 / 11800	MPa	ISO 527-1/-2
Tensile modulus (120°C)	6000 / -	MPa	ISO 527-1/-2
Tensile modulus (160°C)	3100	MPa	ISO 527-1/-2
Stress at break	110 / 100	MPa	ISO 527-1/-2
Stress at break (120°C)	57 / -	MPa	ISO 527-1/-2
Stress at break (160°C)	37	MPa	ISO 527-1/-2
Strain at break	1.6 / 1.6	%	ISO 527-1/-2
Strain at break (120°C)	3 / -	%	ISO 527-1/-2
Strain at break (160°C)	5	%	ISO 527-1/-2
Flexural modulus	11300 / 11600	MPa	ISO 178
Flexural strength	165 / 150	MPa	ISO 178
Flexural modulus (120°C)	6400	MPa	ISO 178
Flexural modulus (160°C)	3600	MPa	ISO 178
Charpy impact strength (+23°C)	26 / 26	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	3 / 3	kJ/m²	ISO 179/1eA

All the trademarks mentioned here are trademarks of Envalior.  
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

ForTii<sup>®</sup> LDS51B

Print Date: 2024-03-27

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES			
DRY / COND			
Melting temperature (10°C/min)	325 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	290 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3	E-4/°C	ASTM D696
Coeff. of linear therm. expansion (normal)	0.4	E-4/°C	ASTM D696
ELECTRICAL PROPERTIES			
DRY / COND			
Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 62631-3-1
Comparative tracking index	400 / -	V	IEC 60112
Relative permittivity (1GHz)	4.13 / 4.23	-	IEC 61189-2-721
OTHER PROPERTIES			
DRY / COND			
Humidity absorption	1.3 / *	%	Sim. to ISO 62
Density	1580 / -	kg/m³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.  
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.