

ForTii[®] LDS85B

PPA–GF30

30% Glass Reinforced, PA4T, Laser Direct Structuring (LDS)

Print Date: 2024–09–17

ForTii[®] LDS85B enables mechanical function integration with high impact resistance and ductility. LDS85B has very good plating performance.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.33 / *	%	ISO 294–4
Molding shrinkage (normal)	1.3 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	10000 / 10000	MPa	ISO 527–1/–2
Tensile modulus (120°C)	5600 / –	MPa	ISO 527–1/–2
Tensile modulus (160°C)	3000	MPa	ISO 527–1/–2
Stress at break	125 / 105	MPa	ISO 527–1/–2
Stress at break (120°C)	64 / –	MPa	ISO 527–1/–2
Stress at break (160°C)	45	MPa	ISO 527–1/–2
Strain at break	2.1 / 2.1	%	ISO 527–1/–2
Strain at break (120°C)	4 / –	%	ISO 527–1/–2
Strain at break (160°C)	6	%	ISO 527–1/–2
Flexural modulus	9400 / 9600	MPa	ISO 178
Flexural strength	185 / 165	MPa	ISO 178
Flexural modulus (120°C)	5400	MPa	ISO 178
Flexural modulus (160°C)	3100	MPa	ISO 178
Charpy impact strength (+23°C)	35 / 35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / 3.6	kJ/m ²	ISO 179/1eA

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

ForTii[®] LDS85B

Print Date: 2024-09-17

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
THERMAL PROPERTIES			
<i>DRY / COND</i>			
Melting temperature (10°C/min)	325 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	285 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.18 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	–	–
ELECTRICAL PROPERTIES			
<i>DRY / COND</i>			
Relative permittivity (1GHz)	3.78 / 3.85	–	IEC 61189-2-721
OTHER PROPERTIES			
<i>DRY / COND</i>			
Humidity absorption	1.4 / *	%	Sim. to ISO 62
Density	1510 / –	kg/m ³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.