

# ForTii<sup>®</sup> MX15HR

## PPA–GF35

35% Glass Fiber Reinforced, PA4T, Electro–friendly, for Automotive applications

Print Date: 2026–06–19

ForTii<sup>®</sup> MX15HR exhibits enhanced hydrolytic stability towards aggressive coolants (water/glycol, 135°C) that are used in engine's thermal management systems. It has excellent mechanical performance and weld–line resistance.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Molding shrinkage (parallel)	0.35 / *	%	ISO 294–4
Molding shrinkage (normal)	1.05 / *	%	ISO 294–4
<b>MECHANICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Tensile modulus	12500 / 12900	MPa	ISO 527–1/–2
Tensile modulus (–40°C)	12500 / –	MPa	ISO 527–1/–2
Tensile modulus (40°C)	12200 / –	MPa	ISO 527–1/–2
Tensile modulus (80°C)	11900 / –	MPa	ISO 527–1/–2
Tensile modulus (100°C)	11600 / 5000	MPa	ISO 527–1/–2
Tensile modulus (120°C)	11200 / 4600	MPa	ISO 527–1/–2
Tensile modulus (150°C)	5300	MPa	ISO 527–1/–2
Tensile modulus (160°C)	4600	MPa	ISO 527–1/–2
Tensile modulus (180°C)	4000	MPa	ISO 527–1/–2
Tensile modulus (200°C)	3700	MPa	ISO 527–1/–2
Stress at break	240 / 220	MPa	ISO 527–1/–2
Stress at break (–40°C)	260 / –	MPa	ISO 527–1/–2
Stress at break (40°C)	220 / –	MPa	ISO 527–1/–2
Stress at break (80°C)	190 / –	MPa	ISO 527–1/–2
Stress at break (100°C)	170 / 76	MPa	ISO 527–1/–2
Stress at break (120°C)	145 / 68	MPa	ISO 527–1/–2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data

# ForTii<sup>®</sup> MX15HR

Print Date: 2026-06-19

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Stress at break (150°C)	80	MPa	ISO 527-1/-2
Stress at break (160°C)	78	MPa	ISO 527-1/-2
Stress at break (180°C)	63	MPa	ISO 527-1/-2
Stress at break (200°C)	55	MPa	ISO 527-1/-2
Strain at break	2.6 / 2.4	%	ISO 527-1/-2
Strain at break (-40°C)	2.7 / -	%	ISO 527-1/-2
Strain at break (40°C)	2.5 / -	%	ISO 527-1/-2
Strain at break (80°C)	2.6 / -	%	ISO 527-1/-2
Strain at break (100°C)	2.7 / 6.6	%	ISO 527-1/-2
Strain at break (120°C)	2.8 / 6.3	%	ISO 527-1/-2
Strain at break (150°C)	8	%	ISO 527-1/-2
Strain at break (160°C)	8	%	ISO 527-1/-2
Strain at break (180°C)	8	%	ISO 527-1/-2
Strain at break (200°C)	8	%	ISO 527-1/-2
Flexural modulus	12000 / 12500	MPa	ISO 178
Flexural strength	320 / 290	MPa	ISO 178
Flexural modulus (120°C)	10900	MPa	ISO 178
Flexural modulus (160°C)	4300	MPa	ISO 178
Flexural modulus (180°C)	3900	MPa	ISO 178
Flexural modulus (200°C)	3700	MPa	ISO 178
Charpy impact strength (+23°C)	76 / 65	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	72 / 63	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 10	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	11 / 9	kJ/m <sup>2</sup>	ISO 179/1eA
<b><i>THERMAL PROPERTIES</i></b>	<b><i>DRY / COND</i></b>		
Melting temperature (10°C/min)	330 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	300 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.16 / *	E-4/°C	ISO 11359-1/-2

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data

# ForTii<sup>®</sup> MX15HR

Print Date: 2026-06-19

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Coeff. of linear therm. expansion (normal)	0.51 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
UL recognition	No / *	–	–
Thermal Index 5000 hrs	170	°C	IEC 60216/ISO 527-1/-2

### *ELECTRICAL PROPERTIES*

#### *DRY / COND*

Volume resistivity	>1E13 / >1E13	Ohm*m	IEC 62631-3-1
Electric strength	35 / 35	kV/mm	IEC 60243-1
Comparative tracking index	600 / –	V	IEC 60112

### *OTHER PROPERTIES*

#### *DRY / COND*

Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1490 / –	kg/m <sup>3</sup>	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.