

Novamid[®] 1013GH30 1 NA/BK701

PA6–GF30

30% Glass Reinforced, Heat Stabilized, Injection Molding

Print Date: 2024–03–27

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294–4
Molding shrinkage (normal)	1 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	9600 / 6000	MPa	ISO 527–1/–2
Stress at break	170 / 110	MPa	ISO 527–1/–2
Strain at break	3.3 / 5	%	ISO 527–1/–2
Flexural modulus	9200 / 5800	MPa	ISO 178
Flexural strength	260 / 170	MPa	ISO 178
Charpy impact strength (+23°C)	81 / 90	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 19	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	205 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.3 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.7 / *	E–4/°C	ISO 11359–1/–2
ELECTRICAL PROPERTIES			
	DRY / COND		
Relative permittivity (100Hz)	4 / –	–	IEC 62631–2–1
Relative permittivity (1 MHz)	4 / –	–	IEC 62631–2–1
Dissipation factor (100 Hz)	140 / –	E–4	IEC 62631–2–1

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Novamid[®] 1013GH30 1 NA/BK701

Print Date: 2024-03-27

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Dissipation factor (1 MHz)	210 / –	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / –	Ohm*m	IEC 62631-3-1
Surface resistivity	– / 2E14	Ohm	IEC 62631-3-2
Electric strength	27 / –	kV/mm	IEC 60243-1
Comparative tracking index	475 / –	V	IEC 60112
<i>OTHER PROPERTIES</i>	<i>DRY / COND</i>		
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1360 / –	kg/m ³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.