

Novamid[®] 2030A-8

PA6/66

Extrusion Grade, Monofilament Grade, Highly lubricated, High Viscosity

Print Date: 2026-04-09

Ideal for high tenacity & high transparency fishing monofilament extrusion.

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>THERMAL PROPERTIES</i>			
<i>DRY / COND</i>			
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
<i>OTHER PROPERTIES</i>			
<i>DRY / COND</i>			
Water absorption	11.4 / *	%	Sim. to ISO 62
Humidity absorption	3.1 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
<i>MATERIAL SPECIFIC PROPERTIES</i>			
<i>DRY / COND</i>			
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid® 2030A-8

Print Date: 2026-04-09

Viscosity-shear rate

