

Novamid[®] 2030CA FC

PA6/66

Film Extrusion, Lubricated, Nucleated, High Viscosity, Food Contact Quality

Print Date: 2026-04-09

Ideal for film extrusion processing.
 Food Contact quality.
 Enhance flexibility, transparency and stretch-ability of the film.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES			
	<i>DRY / COND</i>		
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
	<i>DRY / COND</i>		
Water absorption	11.4 / *	%	Sim. to ISO 62
Humidity absorption	3.1 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
	<i>DRY / COND</i>		
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid® 2030CA FC

Print Date: 2026-04-09

Viscosity-shear rate

