

# Novamid<sup>®</sup> 2030J

## PA6/66

Extrusion Grade, Film Extrusion, Food Contact Quality, no additives

Print Date: 2024-10-25

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b>THERMAL PROPERTIES</b>			
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
<b>OTHER PROPERTIES</b>			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m <sup>3</sup>	ISO 1183
<b>MATERIAL SPECIFIC PROPERTIES</b>			
Viscosity number	246 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

# Novamid<sup>®</sup> 2030J

Print Date: 2024-10-25

## Viscosity-shear rate

