

# Novamid<sup>®</sup> 2430A-1

## PA6/66

Extrusion, Film Extrusion, Lubricated, Food Contact Quality

Print Date: 2026-04-09

Ideal for film extrusion processing.  
 Food Contact quality.  
 Enhance flexibility, transparency and stretch-ability of the film.

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b>THERMAL PROPERTIES</b>			
	<i>DRY / COND</i>		
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
<b>OTHER PROPERTIES</b>			
	<i>DRY / COND</i>		
Humidity absorption	3.5 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m <sup>3</sup>	ISO 1183
<b>MATERIAL SPECIFIC PROPERTIES</b>			
	<i>DRY / COND</i>		
Viscosity number	246 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

# Novamid<sup>®</sup> 2430A-1

Print Date: 2026-04-09

## Viscosity-shear rate

