

# Novamid<sup>®</sup> 2430A

## PA6/66

Extrusion Grade, Monofilament Grade, Highly lubricated, High Viscosity

Print Date: 2024-09-17


Ideal for high tenacity & high transparency fishing monofilament extrusion.  
High viscosity and high 66 content for larger diameter filament.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>THERMAL PROPERTIES</b>			
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
<b>OTHER PROPERTIES</b>			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m <sup>3</sup>	ISO 1183
<b>MATERIAL SPECIFIC PROPERTIES</b>			
Viscosity number	246 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

# Novamid<sup>®</sup> 2430A

Print Date: 2024-09-17

## Viscosity-shear rate



All the trademarks mentioned here are trademarks of Envalior.  
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.