

Novamid[®] 2430A

PA6/66

Extrusion Grade, Monofilament Grade, Highly lubricated, High Viscosity

Print Date: 2026-04-09

Ideal for high tenacity & high transparency fishing monofilament extrusion.
 High viscosity and high 66 content for larger diameter filament.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES			
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Humidity absorption	3.5 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid® 2430A

Print Date: 2026-04-09

Viscosity-shear rate

