

Novamid[®] Care N3U

PA6/66

High Viscosity, Film Extrusion, Lubricated, Medical grade, Food Contact Quality

Print Date: 2024-10-25

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES			
<i>DRY / COND</i>			
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
<i>DRY / COND</i>			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
<i>DRY / COND</i>			
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid[®] Care N3U

Print Date: 2024-10-25

Viscosity–shear rate

