

Novamid[®] Care N3U

PA6/66

High Viscosity, Film Extrusion, Lubricated, Medical grade, Food Contact Quality

Print Date: 2026-04-09

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
THERMAL PROPERTIES			
	<i>DRY / COND</i>		
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
	<i>DRY / COND</i>		
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
	<i>DRY / COND</i>		
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid® Care N3U

Print Date: 2026-04-09

Viscosity–shear rate

