

Novamid[®] X21-F07

PA6I/6T

Extrusion, Transparent, Lubricated

Print Date: 2024-03-27

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>MECHANICAL PROPERTIES</i>	<i>DRY / COND</i>		
Tensile modulus	3000 / 3000	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	8 / 8	kJ/m ²	ISO 179/1eA
<i>OTHER PROPERTIES</i>	<i>DRY / COND</i>		
Water absorption	7 / *	%	Sim. to ISO 62
Humidity absorption	1 / *	%	Sim. to ISO 62
Density	1180 / -	kg/m ³	ISO 1183