

Pocan[®] B1301 000000

PBT

Injection Molding, Unreinforced, Food Contact Quality

Print Date: 2024-04-25

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume–flow rate	60	cm³/10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	1.8	%	ISO 294-4
Molding shrinkage (parallel)	1.8	%	ISO 294-4
MECHANICAL PROPERTIES		VALUE	
Tensile modulus	2700	MPa	ISO 527-1/-2
Yield stress	60	MPa	ISO 527-1/-2
Yield strain	9	%	ISO 527-1/-2
Flexural modulus	2650	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Flexural strain at flexural strength	6	%	ISO 178-A
Charpy impact strength (+23°C)	180	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	150	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)		kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)		kJ/m²	ISO 179/1eA
Izod impact strength (+23°C)	125	kJ/m²	ISO 180/1U
Izod impact strength (-30°C)	90	kJ/m²	ISO 180-1U
THERMAL PROPERTIES		VALUE	
Melting temperature (10°C/min)	225	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	65	°C	ISO 75-1/-2

All the trademarks mentioned here are trademarks of Envalior.
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Pocan® B1301 000000

Print Date: 2024-04-25

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Temp. of deflection under load (0.45 MPa)	140	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	1.1	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.1	E-4/°C	ISO 11359-1/-2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Oxygen index	24	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	750	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2	mm	IEC 60695-2-12

ELECTRICAL PROPERTIES	VALUE		
Relative permittivity (100Hz)	3.4	—	IEC 62631-2-1
Relative permittivity (1 MHz)	3.2	—	IEC 62631-2-1
Dissipation factor (100 Hz)	15	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	190	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	600	V	IEC 60112

OTHER PROPERTIES	VALUE		
Water absorption	0.5	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1310	kg/m³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.