

# Pocan<sup>®</sup> DP4035 000000

(PBT+PET)–GF30 FR(40+30)

30% Glass Reinforced, Injection Molding, Flame Retardant (halogen free)

Print Date: 2024–06–28

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	VALUE		
Molding shrinkage (normal)	1	%	ISO 294–4
Molding shrinkage (parallel)	0.3	%	ISO 294–4
<b>MECHANICAL PROPERTIES</b>			
	VALUE		
Tensile modulus	9000	MPa	ISO 527–1/–2
Stress at break	105	MPa	ISO 527–1/–2
Strain at break	2.4	%	ISO 527–1/–2
Flexural modulus	9200	MPa	ISO 178
Flexural strength	170	MPa	ISO 178
Flexural strain at flexural strength	2.8	%	ISO 178–A
Charpy impact strength (+23°C)	40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (–30°C)	30	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)		kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (–30°C)		kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength (+23°C)	35	kJ/m <sup>2</sup>	ISO 180/1U
Izod impact strength (–30°C)	30	kJ/m <sup>2</sup>	ISO 180–1U
<b>THERMAL PROPERTIES</b>			
	VALUE		
Temp. of deflection under load (1.80 MPa)	195	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75–1/–2
Burning Behav. at 1.5 mm nom. thickn.	V–2	class	IEC 60695–11–10
Thickness tested	1.5	mm	IEC 60695–11–10
Oxygen index	24	%	ISO 4589–1/–2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data

# Pocan<sup>®</sup> DP4035 000000

Print Date: 2024-06-28

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Glow Wire Flammability Index GWFI	900	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.75	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	1.5	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	0.75	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	1.5	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695-2-13
GWIT (Thickness (3) tested)	3	mm	IEC 60695-2-13

### *ELECTRICAL PROPERTIES*

#### *VALUE*

Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	33	kV/mm	IEC 60243-1
Comparative tracking index	475	V	IEC 60112

### *OTHER PROPERTIES*

#### *VALUE*

Water absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1620	kg/m <sup>3</sup>	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.


Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

# Pocan<sup>®</sup> DP4035 000000

Print Date: 2024-06-28

## Viscosity-shear rate



All the trademarks mentioned here are trademarks of Envalior.  
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.  
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.  
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.  
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.