

Pocan[®] ECOT3220

(PBT+PET)–GF20

20% Glass Fiber Reinforced, Injection Molding, Excellent Surface Properties, Recycled Content

Print Date: 2025–10–14

Sustainability

Mass balanced
Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume–flow rate	15	cm³/10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	1	%	ISO 294–4
Molding shrinkage (parallel)	0.4	%	ISO 294–4
MECHANICAL PROPERTIES		VALUE	
Tensile modulus	7500	MPa	ISO 527–1/–2
Stress at break	120	MPa	ISO 527–1/–2
Strain at break	3.2	%	ISO 527–1/–2
Flexural modulus	7500	MPa	ISO 178
Flexural strength	195	MPa	ISO 178
Flexural strain at flexural strength	3.5	%	ISO 178–A
Charpy impact strength (+23°C)	40	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	35	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	6	kJ/m²	ISO 179/1eA
Izod impact strength (+23°C)	35	kJ/m²	ISO 180/1U
Izod impact strength (–30°C)	35	kJ/m²	ISO 180–1U

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Pocan[®] ECOT3220

Print Date: 2025-10-14

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES		VALUE	
Temp. of deflection under load (1.80 MPa)	195	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.9	E-4/°C	ISO 11359-1/-2
ELECTRICAL PROPERTIES		VALUE	
Comparative tracking index	225	V	IEC 60112
OTHER PROPERTIES		VALUE	
Water absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1470	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS		VALUE	
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4-8	h	
Residual moisture content	0.00-0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260-280	°C	
Mold temperature	80-100	°C	

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.