

Pocan[®] T7391 POS151

(PBT+PET)–GF45

45% Glass Reinforced, Injection Molding, UV Stabilized, Excellent Surface Properties

Print Date: 2024–10–08

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume–flow rate	30	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	5	kg	ISO 1133
Molding shrinkage (normal)	0.8	%	ISO 294–4
Molding shrinkage (parallel)	0.2	%	ISO 294–4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	16000	MPa	ISO 527–1/–2
Stress at break	160	MPa	ISO 527–1/–2
Strain at break	1.9	%	ISO 527–1/–2
Flexural modulus	15500	MPa	ISO 178
Flexural strength	260	MPa	ISO 178
Flexural strain at flexural strength	2.1	%	ISO 178–A
Charpy impact strength (+23°C)	60	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	65	kJ/m ²	ISO 179/1eU
Izod impact strength (+23°C)	55	kJ/m ²	ISO 180/1U
THERMAL PROPERTIES			
	VALUE		
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	225	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.2	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.8	E–4/°C	ISO 11359–1/–2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695–11–10

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Pocan[®] T7391 POS151

Print Date: 2024-10-08

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Oxygen index	21	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	750	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2	mm	IEC 60695-2-12

<i>ELECTRICAL PROPERTIES</i>	<i>VALUE</i>		
Relative permittivity (100Hz)	4.3	–	IEC 62631-2-1
Relative permittivity (1 MHz)	4.2	–	IEC 62631-2-1
Dissipation factor (100 Hz)	20	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	140	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	28	kV/mm	IEC 60243-1

<i>OTHER PROPERTIES</i>	<i>VALUE</i>		
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1690	kg/m ³	ISO 1183

<i>PROCESSING RECOMMENDATIONS</i>	<i>VALUE</i>		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4-8	h	
Residual moisture content	0.00-0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260-280	°C	
Mold temperature	80-100	°C	

All the trademarks mentioned here are trademarks of Envialor.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envialor 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envialor.