

Stanyl[®] HGR3–W

PA46

Heat Stabilized, PFAS–free, Wear and Friction Modified

Print Date: 2026–04–03

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
RHEOLOGICAL PROPERTIES			
	<i>DRY / COND</i>		
Molding shrinkage [parallel]	2 / *	%	Sim. to ISO 294–4
Molding shrinkage [normal]	2 / *	%	Sim. to ISO 294–4
MECHANICAL PROPERTIES			
	<i>DRY / COND</i>		
Tensile modulus	2500 / 700	MPa	ISO 527–1/–2
Tensile modulus (120°C)	560 / –	MPa	ISO 527–1/–2
Tensile modulus (160°C)	420	MPa	ISO 527–1/–2
Yield stress	75 / –	MPa	ISO 527–1/–2
Nominal strain at break	35 / –	%	ISO 527–1/–2
Nominal strain at break (120°C)	>50	%	ISO 527–1/–2
Nominal strain at break (160°C)	>50	%	ISO 527–1/–2
Stress at break	– / 60	MPa	ISO 527–1/–2
Stress at break (120°C)	45 / –	MPa	ISO 527–1/–2
Stress at break (160°C)	33	MPa	ISO 527–1/–2
Flexural modulus	2350 / 650	MPa	ISO 178
Flexural strength	93 / 19	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	22 / 130	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	14 / 16	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	<i>DRY / COND</i>		
Melting temperature (10°C/min)	295 / *	°C	ISO 11357–1/–3

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Stanyl® HGR3–W

Print Date: 2026–04–03

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Temp. of deflection under load (1.80 MPa)	75 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	240 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.9 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	1.1 / *	E–4/°C	ISO 11359–1/–2
<i>OTHER PROPERTIES</i>	<i>DRY / COND</i>		
Humidity absorption	3.7 / *	%	Sim. to ISO 62
Density	1140 / –	kg/m ³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2026. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.