

# Stanyl<sup>®</sup> KS411 B–MB

## PA46

Extrusion Grade

Print Date: 2026–04–09

### Sustainability

Bio-based  
Mass balanced

| PROPERTIES                     | TYPICAL DATA | UNIT              | TEST METHOD    |
|--------------------------------|--------------|-------------------|----------------|
| <b>THERMAL PROPERTIES</b>      |              |                   |                |
| Melting temperature (10°C/min) | 287 / *      | °C                | ISO 11357–1/–3 |
| <b>OTHER PROPERTIES</b>        |              |                   |                |
| Humidity absorption            | 3.7 / *      | %                 | Sim. to ISO 62 |
| Density                        | 1180 / –     | kg/m <sup>3</sup> | ISO 1183       |