

Stanyl® TS272A1

(PA46+PTFE)–AF

Aramid fibre reinforced, Wear and Friction Modified

Print Date: 2024–09–17

Stanyl® TS272A1 is a aramid–reinforced friction–modified high heat polyamide that offers extremely low abrasion for gear & bushing applications

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	2.2 / *	%	ISO 294–4
Molding shrinkage (normal)	2.2 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	2800 / 1100	MPa	ISO 527–1/–2
Tensile modulus (120°C)	780 / –	MPa	ISO 527–1/–2
Tensile modulus (160°C)	630	MPa	ISO 527–1/–2
Tensile modulus (180°C)	590	MPa	ISO 527–1/–2
Tensile modulus (200°C)	560	MPa	ISO 527–1/–2
Yield stress	* / 50	MPa	ISO 527–1/–2
Yield stress (120°C)	44	MPa	ISO 527–1/–2
Yield stress (160°C)	36	MPa	ISO 527–1/–2
Yield stress (180°C)	33	MPa	ISO 527–1/–2
Yield stress (200°C)	30	MPa	ISO 527–1/–2
Nominal strain at break	* / >50	%	ISO 527–1/–2
Nominal strain at break (120°C)	>50	%	ISO 527–1/–2
Nominal strain at break (160°C)	>50	%	ISO 527–1/–2
Nominal strain at break (180°C)	>50	%	ISO 527–1/–2
Nominal strain at break (200°C)	>50	%	ISO 527–1/–2
Stress at break	80 / *	MPa	ISO 527–1/–2
Strain at break	16 / *	%	ISO 527–1/–2

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Stanyl® TS272A1

Print Date: 2024-09-17

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Flexural modulus	2800 / –	MPa	ISO 178
Flexural modulus (120°C)	800	MPa	ISO 178
Flexural modulus (160°C)	700	MPa	ISO 178
Flexural strength	100 / –	MPa	ISO 178
Flexural strength (120°C)	25	MPa	ISO 178
Flexural strength (160°C)	20	MPa	ISO 178
Charpy impact strength (+23°C)	87 / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	60 / 63	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5 / 5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	3 / 3	kJ/m ²	ISO 179/1eA
<i>THERMAL PROPERTIES</i>	<i>DRY / COND</i>		
Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	160 / *	°C	ISO 75-1/-2
<i>OTHER PROPERTIES</i>	<i>DRY / COND</i>		
Humidity absorption	3 / *	%	Sim. to ISO 62
Density	1260 / –	kg/m ³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.