

# Stanyl® TW241B3

## PA46–CF15

15% Carbon Reinforced, Heat Stabilized, Lubricated

Print Date: 2024–09–17

Stanyl® TW241B3 is a high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle–time advantages and excellent flow. TW241B3 has an excellent track–record in gear applications.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294–4
Molding shrinkage (normal)	1.1 / *	%	ISO 294–4
<b>MECHANICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Tensile modulus	13000 / 7000	MPa	ISO 527–1/–2
Tensile modulus (120°C)	6800 / –	MPa	ISO 527–1/–2
Tensile modulus (160°C)	6400	MPa	ISO 527–1/–2
Tensile modulus (180°C)	6100	MPa	ISO 527–1/–2
Tensile modulus (200°C)	5200	MPa	ISO 527–1/–2
Stress at break	210 / 130	MPa	ISO 527–1/–2
Stress at break (120°C)	100 / –	MPa	ISO 527–1/–2
Stress at break (160°C)	87	MPa	ISO 527–1/–2
Stress at break (180°C)	81	MPa	ISO 527–1/–2
Stress at break (200°C)	75	MPa	ISO 527–1/–2
Strain at break	2.3 / 4.3	%	ISO 527–1/–2
Strain at break (120°C)	3.3 / –	%	ISO 527–1/–2
Strain at break (160°C)	3.2	%	ISO 527–1/–2
Strain at break (180°C)	3.2	%	ISO 527–1/–2
Strain at break (200°C)	3.6	%	ISO 527–1/–2
Flexural modulus	11500 / 5800	MPa	ISO 178

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## Property Data

# Stanyl® TW241B3

Print Date: 2024-09-17

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Flexural modulus (120°C)	5800	MPa	ISO 178
Flexural modulus (160°C)	5500	MPa	ISO 178
Flexural strength	290 / 150	MPa	ISO 178
Flexural strength (120°C)	140	MPa	ISO 178
Flexural strength (160°C)	125	MPa	ISO 178
Charpy impact strength (+23°C)	45 / 70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	40 / 40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	5.5 / 12	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	4.5 / 4.5	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength (+23°C)	5.5 / 12	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength (-40°C)	4.5 / 4.5	kJ/m <sup>2</sup>	ISO 180/1A

### THERMAL PROPERTIES

#### DRY / COND

Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	290 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.25 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.5 / *	E-4/°C	ISO 11359-1/-2

### ELECTRICAL PROPERTIES

#### DRY / COND

Volume resistivity	100000 / -	Ohm*m	IEC 62631-3-1
--------------------	------------	-------	---------------

### OTHER PROPERTIES

#### DRY / COND

Humidity absorption	3.2 / *	%	Sim. to ISO 62
Density	1230 / -	kg/m <sup>3</sup>	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.