

Stanyl® TW241F3

PA46–GF15

15% Glass Reinforced, Heat Stabilized, Lubricated

Print Date: 2024–09–17

Stanyl® TW241F3 is a high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance especially at high temperatures, in combination with cycle–time advantages and excellent flow.

| PROPERTIES | TYPICAL DATA | UNIT | TEST METHOD |
|------------------------------|-------------------|------|--------------|
| MECHANICAL PROPERTIES | | | |
| | DRY / COND | | |
| Tensile modulus | 6100 / 2800 | MPa | ISO 527–1/–2 |
| Tensile modulus (120°C) | 3000 / – | MPa | ISO 527–1/–2 |
| Tensile modulus (160°C) | 2650 | MPa | ISO 527–1/–2 |
| Tensile modulus (180°C) | 2500 | MPa | ISO 527–1/–2 |
| Tensile modulus (200°C) | 2350 | MPa | ISO 527–1/–2 |
| Stress at break | 140 / 85 | MPa | ISO 527–1/–2 |
| Stress at break (120°C) | 82 / – | MPa | ISO 527–1/–2 |
| Stress at break (160°C) | 74 | MPa | ISO 527–1/–2 |
| Stress at break (180°C) | 70 | MPa | ISO 527–1/–2 |
| Stress at break (200°C) | 66 | MPa | ISO 527–1/–2 |
| Strain at break | 3.5 / 12 | % | ISO 527–1/–2 |
| Strain at break (120°C) | 13 / – | % | ISO 527–1/–2 |
| Strain at break (160°C) | 12 | % | ISO 527–1/–2 |
| Strain at break (180°C) | 12 | % | ISO 527–1/–2 |
| Strain at break (200°C) | 12 | % | ISO 527–1/–2 |
| Flexural modulus | 5800 / 2800 | MPa | ISO 178 |
| Flexural modulus (120°C) | 2700 | MPa | ISO 178 |
| Flexural modulus (160°C) | 2600 | MPa | ISO 178 |
| Flexural strength | 235 / 125 | MPa | ISO 178 |
| Flexural strength (120°C) | 80 | MPa | ISO 178 |
| Flexural strength (160°C) | 75 | MPa | ISO 178 |

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Stanyl® TW241F3

Print Date: 2024-09-17

| <i>PROPERTIES</i> | <i>TYPICAL DATA</i> | <i>UNIT</i> | <i>TEST METHOD</i> |
|--|---------------------|-------------------|--------------------|
| Charpy impact strength (+23°C) | 50 / 100 | kJ/m ² | ISO 179/1eU |
| Charpy impact strength (-30°C) | 45 / 50 | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength (+23°C) | 6 / 13 | kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength (-30°C) | 6 / 6 | kJ/m ² | ISO 179/1eA |
| Izod notched impact strength (+23°C) | 6 / 13 | kJ/m ² | ISO 180/1A |
| Izod notched impact strength (-40°C) | 6 / 6 | kJ/m ² | ISO 180/1A |

| <i>THERMAL PROPERTIES</i> | <i>DRY / COND</i> | | |
|--|-------------------|--------|-----------------|
| Melting temperature (10°C/min) | 295 / * | °C | ISO 11357-1/-3 |
| Temp. of deflection under load (1.80 MPa) | 275 / * | °C | ISO 75-1/-2 |
| Temp. of deflection under load (0.45 MPa) | 290 / * | °C | ISO 75-1/-2 |
| Coeff. of linear therm. expansion (parallel) | 0.5 / * | E-4/°C | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion (normal) | 0.8 / * | E-4/°C | ISO 11359-1/-2 |
| Burning Behav. at 3.0 mm nom. thickn. | HB / * | class | IEC 60695-11-10 |
| Thickness tested | 3 / * | mm | IEC 60695-11-10 |
| UL recognition | Yes / * | - | - |
| Relative Temperature Index – electrical | 65 | °C | UL746B |
| RTI electrical (Thickness (1) tested) | 0.75 | mm | UL746B |

| <i>OTHER PROPERTIES</i> | <i>DRY / COND</i> | | |
|-------------------------|-------------------|-------------------|----------------|
| Humidity absorption | 3.15 / * | % | Sim. to ISO 62 |
| Density | 1290 / - | kg/m ³ | ISO 1183 |

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.


Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Stanyl® TW241F3

Print Date: 2024-09-17

Tens. fatigue 8Hz, T, R=0.1 ,
dry



All the trademarks mentioned here are trademarks of Envalior.
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.