

Stanyl® TW241F3

PA46–GF15

15% Glass Fiber Reinforced, Heat Stabilized, Lubricated

Print Date: 2025–10–04

Stanyl® TW241F3 is a high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance especially at high temperatures, in combination with cycle–time advantages and excellent flow.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES		DRY / COND	
Tensile modulus	6100 / 2800	MPa	ISO 527–1/–2
Tensile modulus (120°C)	3000 / –	MPa	ISO 527–1/–2
Tensile modulus (160°C)	2650	MPa	ISO 527–1/–2
Tensile modulus (180°C)	2500	MPa	ISO 527–1/–2
Tensile modulus (200°C)	2350	MPa	ISO 527–1/–2
Stress at break	140 / 85	MPa	ISO 527–1/–2
Stress at break (120°C)	82 / –	MPa	ISO 527–1/–2
Stress at break (160°C)	74	MPa	ISO 527–1/–2
Stress at break (180°C)	70	MPa	ISO 527–1/–2
Stress at break (200°C)	66	MPa	ISO 527–1/–2
Strain at break	3.5 / 12	%	ISO 527–1/–2
Strain at break (120°C)	13 / –	%	ISO 527–1/–2
Strain at break (160°C)	12	%	ISO 527–1/–2
Strain at break (180°C)	12	%	ISO 527–1/–2
Strain at break (200°C)	12	%	ISO 527–1/–2
Flexural modulus	5800 / 2800	MPa	ISO 178
Flexural modulus (120°C)	2700	MPa	ISO 178
Flexural modulus (160°C)	2600	MPa	ISO 178
Flexural strength	235 / 125	MPa	ISO 178
Flexural strength (120°C)	80	MPa	ISO 178
Flexural strength (160°C)	75	MPa	ISO 178

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Stanyl® TW241F3

Print Date: 2025-10-04

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Charpy impact strength (+23°C)	50 / 100	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	45 / 50	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6 / 13	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	6 / 6	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	6 / 13	kJ/m²	ISO 180/1A
Izod notched impact strength (-40°C)	6 / 6	kJ/m²	ISO 180/1A

THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	275 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	290 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.5	E-4/°C	ASTM D696
Coeff. of linear therm. expansion (normal)	0.8	E-4/°C	ASTM D696
Thermal conductivity in plane	0.33	W/(m K)	ASTM E1461
Thermal conductivity through plane	0.29	W/(m K)	ASTM E1461
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	—	—
Relative Temperature Index – electrical	65	°C	UL746B
RTI electrical (Thickness (1) tested)	0.75	mm	UL746B


OTHER PROPERTIES	DRY / COND		
Humidity absorption	3.15 / *	%	Sim. to ISO 62
Density	1290 / —	kg/m³	ISO 1183

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Stanyl® TW241F3

Print Date: 2025-10-04

Tens. fatigue 8Hz, T, R=0.1 ,
dry



Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2025. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.